

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 241 432 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

18.09.2002 Bulletin 2002/38

(51) Int Cl.7: **F41H 5/04**

(21) Application number: **01200979.1**

(22) Date of filing: **15.03.2001**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**

Designated Extension States:

AL LT LV MK RO SI

(71) Applicant: **Teijin Twaron GmbH**

42103 Wuppertal (DE)

(72) Inventors:

• **Fels, Achim**

42109 Wuppertal (DE)

• **Böttger, Christian**

42897 Remscheid (DE)

• **Baumgart, Christoph**

45549 Sprockhövel (DE)

• **Dorloff-Lumpe, Bärbel**

42113 Wuppertal (DE)

(74) Representative: **Fett, Günter**

CPW GmbH

Kasinostrasse 19 - 21

42103 Wuppertal (DE)

(54) **Penetration-resistant material comprising fabric with high linear density ratio of two sets of threads**

(57) The invention pertains to a penetration-resistant material comprising at least a double layer of woven fabric, characterized in that the double layer comprises a first layer of fabric composed of a first set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65% of the fabric weight, and a second set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, with the second set of threads being transverse to the first set of threads, and the ratio of the number of threads/cm of the first set to that of the second set is > 1 , and a second layer of fabric composed of a

first set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, and a second set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65% of the fabric weight, with the second set of threads being transverse to the first set of threads, and the ratio of the number of threads/cm of the second set to that of the first set is > 1 , and wherein the first and second sets of threads of the first layer have a parallel orientation towards the first and second sets, respectively, of threads of the second layer.

EP 1 241 432 A1

Description

[0001] The invention pertains to penetration-resistant material comprising a double layer of fabric with high linear density ratios of two sets of threads, and to articles made of the same.

[0002] Penetration-resistant articles such as bullet-proof vests, helmets, vehicle panels, and shields prepared from high strength fibers are known in the art. For many applications, in particular for ballistic vests, the fibers are used in a woven or knitted fabric. These fabrics may be coated or impregnated in a matrix to obtain hard ballistic materials, or may be used free from matrix to obtain soft ballistic materials.

Bulletproof woven fabrics are known, *inter alia*, from EP 310,199. The fabrics disclosed therein are composed of filament yarns of ultrahigh molecular weight polymer having high strength and high modulus, with the warp threads being of a different polymeric material than the weft threads.

In Russian patent RU 2,096,542 a ballistic fabric for bulletproof jackets was disclosed having warp and weft threads of poly para-phenyleneterephthalamide (PPTA) wherein the ratio of warp to weft linear density is smaller than 4.17. Typically, warp threads having a linear density of 143 to 588 dtex and weft threads having a linear density of 588 to 930 were disclosed, the weft threads having equal or higher linear density than the warp threads. It is particularly contended that ballistic fabrics having warp to weft linear density ratios between 1.59 and 4.17 have improved deflection properties.

In WO 00/42246 a penetration-resistant material is disclosed comprising at least a double layer of fabric composed of two layers of woven fabric which are cross-plyied at an angle wherein the fabric is composed of a first set of threads comprising 3.5 to 20 threads/cm and having a linear density of at least 420 dtex, and a second set of threads comprising 0.5 to 8 threads/cm and having a linear density of at least 50 dtex, with the second set of threads being transverse to the first set of threads, and wherein the ratio of the linear density of the first set of threads to the linear density of the second set of threads is > 4.2 , more preferably > 7.5 . In a preferred embodiment the first set of threads is warp threads made of p-aramid yarn and the second set of threads is weft threads of polyester yarn, and the ratio of the number of threads/cm of the first set to that of the second set is > 1 . Although the ballistic performance of this article is excellent, the necessity of cross-plying the layers is a disadvantage in terms of ease and simplicity of the manufacture and the danger of creating weak points, that inherently to the process of cross-plying can occur.

[0003] It has now been found that penetration-resistant materials with the advantages of the prior art materials but without their disadvantages can be made.

To this end a penetration-resistant material is claimed comprising at least a double layer of woven fabric, characterized in that the double layer comprises a first layer

of fabric composed of a first set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65% of the fabric weight, and a second set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, with the second set of threads being transverse to the first set of threads, and the ratio of the number of threads/cm of the first set to that of the second set is > 1 , and a second layer of fabric composed of a first set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, and a second set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65% of the fabric weight, with the second set of threads being transverse to the first set of threads, and the ratio of the number of threads/cm of the second set to that of the first set is > 1 , and wherein the first and second sets of threads of the first layer have a parallel orientation towards the first and second sets, respectively, of threads of the second layer.

[0004] Preferably, the penetration-resistant material has at least a ratio of the linear density of the first set of threads to the linear density of the second set of threads of the first layer and of the linear density of the second set of threads to the linear density of the first set of threads of the second layer is > 1 , more preferably > 4.2 , and most preferably > 5.9 . A particularly effective ratio is 6-6.6. The number of threads in the first set of threads of the first layer and the second set of threads of the second layer is 3.5 to 20 threads/cm. More preferably, the number is 4 to 15 threads/cm, and most preferably 5 to 12 threads/cm. The number of threads in the second set of threads of the first layer and the first set of threads of the second layer is 0.5 to 16 threads/cm. Preferably, the number is 0.5 to 8, more preferably 1 to 6 threads/cm, and most preferably 2 to 4 threads/cm. In each layer the threads having a linear density of at least 210 dtex comprise at least 65% of the fabric weight of that layer. Preferably, these threads comprise at least 70%, and more preferably 75% of the fabric weight of that layer. For reasons of efficient manufacturing it is preferred that the first set of threads of the first layer and the first set of threads of the second layer are of warp threads and the second set of threads of the first layer and the second set of threads of the second layer are weft threads. The second set of threads is transverse to the first set of threads in each of the two layers. Although usually these sets are about perpendicular to each other, but this is not necessary. The second set of threads may be provided under at angle other than 90° to the first set of threads. The two layers are secured together without cross-plying.

[0005] The penetration-resistant material also consists of a second set of threads of the first layer (preferably weft threads) and a first set of threads of the second layer (preferably warp threads), the yarn composition of which is not decisive for the present invention. Preferably, however, these threads have high strength and high

modulus. This is particularly the case when these threads are selected from polyester, polyethylene, polypropylene, polyamide, and aramid yarn. Most preferably, the second set of threads of the first layer and the first set of threads of the second layer is made of polyester yarn.

The first set of threads of the first layer (preferably warp threads) and the second set of threads of the second layer (preferably weft threads) are of high strength and high modulus, and most preferably high tenacity threads from aramid, polyethylene, and poly-p-phenylenebenzobisoxazole (PBO) yarn are selected, more particularly p-aramid. Most preferred is poly para-phenyleneterephthalamide (PPTA). In a preferred embodiment the warp and weft threads are selected to be made of different polymers, for instance, a fabric having warp threads of p-aramid yarn and weft threads of polyester yarn, or reversed, is preferred.

[0006] As long as the required linear density ratio is satisfied, the linear density of the first set of threads of the first layer and the second set of threads of the second layer is selected to be at least about 210 dtex, preferably between 210 and 6720, more preferably between 420 and 3360 dtex, even more preferably between 420 and 1680 dtex, and most preferably between about 840 and 1100 dtex. The linear density of the second set of threads of the first layer and the first set of threads of the second layer is selected to be at least about 50 dtex, more preferably between 50 and 280 dtex, and most preferably between about 80 and 140 dtex.

[0007] The term "thread" means any sort of thread such as staple yarn, twisted staple yarn, twisted filament yarn, non-twisted intermingled yarn, and preferably, untwisted filament yarn.

[0008] In a preferred embodiment the threads of each of the two fabric layers of the double layer are bonded together, for instance, by stitch bonding, or preferably, with an adhesive material. The adhesive material may be adhesive material provided onto the threads or onto the fabric, for instance, as a finish. The adhesive material can also be an adhesive layer provided between the two fabric layers of the double layer. Adhesive materials include thermoplastic, elastomeric, and thermoset materials. It is also possible to use for at least part of the second set of threads of the first layer and the first set of threads of the second layer a material that melts under pressure and/or heating, thereby accomplishing binding the threads of the first set, respectively second set of threads to those of the second set, respectively first set of threads, and optionally also binding the two fabric layers together. Thermoplastic materials include polyolefins such as polyethylene and polypropylene, polyamide, polyester, or mixtures of these materials. Elastomeric materials include Kraton, rubber, silicon, and the like. Thermoset materials include epoxy resins, polyester resins, phenolic resins, vinyl ester resins, and the like.

[0009] In another preferred embodiment at least one

of the outer sides of the penetration-resistant material is provided with a protective layer. The protective layer can be a thermoplastic, thermoset, or an elastomeric material, or a mixture of these materials. The protective layer is applied to protect the fabric from damage by excessive abrasion and to improve the ballistic performance.

[0010] The penetration-resistant material comprises at least one double layer consisting of two layers of woven fabric, which are non-cross-plyed and optionally bonded together. The term woven includes all types of weaves, such as plain weave, satin weave, basket weave, twill weave, and the like. Preferred fabrics are plain woven.

[0011] The penetration-resistant article may contain as little as one double layer consisting of two layers of woven fabric, but usually more double layers are applied. Suitable numbers of double layers are 5 to 100, and most preferably 6 to 35 double layers are used. The first set of threads of the first fabric layer of a double layer may be parallel to, or at an angle to, the first set of threads of the first fabric layer of the adjacent double layer. If these sets are secured together under an angle, such an angle is preferably 90°.

[0012] The double layers are secured together using an adhesive layer or by stitching. Such an adhesive layer may be made of the previously mentioned materials for the adhesive materials and has a thickness between 4 and 36 μ , preferably between 8 and 20 μ .

[0013] Methods of manufacture of the double layers are well known in the art. Usually the fabric is made by warping the warp yarn on a beam, followed by weaving on a loom. The single layer may optionally be impregnated or laminated, and be subjected to a calendering or lamination process. At least two fabric layers can be bonded together by stitching, heating, or applying pressure.

[0014] The invention pertains also to articles like bulletproof vests and armor plates made of the above-mentioned woven fabric according to methods known to the skilled man.

[0015] The invention is further illustrated with the following example.

[0016] A construction was made containing 22 double layers. The first layer of each double layer was produced from Twaron® 930 dtex in warp (9.5 threads/cm) and polyester 140 dtex (Trevira® 710, ex Hoechst) in weft direction (2 threads/cm). The second layer of each double layer was produced from polyester 140 dtex (Trevira® 710, ex Hoechst) in warp direction (4 threads/cm) and Twaron® 930 dtex in weft direction (9.5 threads/cm). The warp/weft ratio of the first layer and the weft/warp ratio of the second layer was 6.6. The layers were laminated together with 3 plies of a polyethylene film (LDPE, ex EKB) having a thickness of 10 μ , one sheet of polyethylene film being placed on both outer sides of the double layer and one sheet of polyethylene film being placed in-between each of the two fabric layers of

the double layer. The total weight of the construction was about 4600 g/m².

V 50 values were determined with 9x19 Para Type DM 11 A1 B2 bullets,

wherein V 50 is the velocity at which 50% of the bullets are stopped and 50% of the bullets give full penetration. It was found, that V 50 of this construction was 507 m/s.

Claims

1. A penetration-resistant material comprising at least a double layer of woven fabric, **characterized in that** the double layer comprises a first layer of fabric composed of a first set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65% of the fabric weight, and a second set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, with the second set of threads being transverse to the first set of threads, and the ratio of the number of threads/cm of the first set to that of the second set is > 1 , and a second layer of fabric composed of a first set of threads comprising 0.5 to 16 threads/cm and having a linear density of at least 50 dtex, and a second set of threads comprising 3.5 to 20 threads/cm, having a linear density of at least 210 dtex, and comprising at least 65% of the fabric weight, with the second set of threads being transverse to the first set of threads, and the ratio of the number of threads/cm of the second set to that of the first set is > 1 , and wherein the first and second sets of threads of the first layer have a parallel orientation towards the first and second sets, respectively, of threads of the second layer.
2. The penetration-resistant material of claim 1 wherein at least the ratio of the linear density of the first set of threads to the linear density of the second set of threads of the first layer and of the linear density of the second set of threads to the linear density of the first set of threads of the second layer is > 1 .
3. The penetration-resistant material of claim 1 wherein at least the ratio of the linear density of the first set of threads to the linear density of the second set of threads of the first layer and of the linear density of the second set of threads to the linear density of the first set of threads of the second layer is > 4.2 .
4. The penetration-resistant material of claim 1 wherein at least the ratio of the linear density of the first set of threads to the linear density of the second set of threads of the first layer and of the linear density of the second set of threads to the linear density of the first set of threads of the second layer is > 5.9 .
5. The penetration-resistant material of any of claims 1-4 wherein at least one of the second set of threads of the first layer and the first set of threads of the second layer comprises 0.5 to 8 threads/cm.
6. The penetration-resistant material of any of claims 1-5 wherein the threads of the layers of the double layer are bonded together, preferably with an adhesive material.
7. The penetration-resistant material of any of claims 1-6 wherein the first set of threads of the first layer and the second set of thread of the second layer consist of high tenacity threads selected from aramid, polyethylene, and poly-p-phenylenebenzobisoxazole (PBO).
8. The penetration-resistant material of any of claims 1-6 wherein the second set of threads of the first layer and the first set of threads of the second layer are selected from polyester, polyethylene, polypropylene, and aramid yarn.
9. The penetration-resistant material of any one of claims 1-8 wherein the first set of threads of the first layer and the second set of threads of the second layer consist of aramid threads, and the second set of threads of the first layer and the first set of threads of the second layer consist of polyester threads.
10. The penetration-resistant material of any one of claims 1-9 wherein the linear density of the first set of threads of the first layer and the second set of threads of the second layer is 210 to 6720, preferably 420 to 3360, more preferably 420 to 1680 dtex, and most preferably 840 to 1100 dtex.
11. The penetration-resistant material of any one of claims 1-10 wherein the linear density of the second set of threads of the first layer and the first set of threads of the second layer is 50 to 280 dtex, and preferably 80-140 dtex.
12. The penetration-resistant material of any one of claims 1-11 wherein the first set of threads of the first layer and the first set of threads of the second layer are warp threads and the second set of threads of the first layer and the second set of threads of the second layer are weft threads.
13. The penetration-resistant material of any one of claims 1-12 wherein at least one of the outer sides of the double layer is provided with a protective layer.
14. An article made of the penetration-resistant material of any one of claims 1-13.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 0979

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X,D	WO 00 42246 A (AKZO NOBEL) 20 July 2000 (2000-07-20) * the whole document *	1-14	F41H5/04
A,D	EP 0 310 199 A (STAMICARBON) 5 April 1989 (1989-04-05) * column 2, line 46 - column 3, line 26; claim 1 *	1-14	
A	US 5 187 003 A (CHITRANGAD) 16 February 1993 (1993-02-16) * abstract; claims 1-12; examples 1,3 *	1-14	
A	US 5 802 607 A (TRIPLETTE) 8 September 1998 (1998-09-08) * abstract; figure 3 *	1	
A	DATABASE WPI Section Ch, Week 199417 Derwent Publications Ltd., London, GB; Class A83, AN 1994-142436 XP002168442 & SU 1 792 517 A (SPECIAL MECH ENG RES INST), 30 January 1993 (1993-01-30) * abstract *	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			F41H
Place of search	Date of completion of the search	Examiner	
THE HAGUE	29 May 2001	Giesen, M	
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons \$: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 52 (P.01/03)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 20 0979

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

29-05-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0042246 A	20-07-2000	AU 2108800 A	01-08-2000
EP 310199 A	05-04-1989	AU 2338088 A	06-04-1989
		BR 8805055 A	09-05-1989
		CN 1035887 A	27-09-1989
		CN 1036418 A	18-10-1989
		JP 1156541 A	20-06-1989
		ZA 8807385 A	28-06-1989
US 5187003 A	16-02-1993	DE 69207780 D	29-02-1996
		DE 69207780 T	08-08-1996
		EP 0615558 A	21-09-1994
		JP 3051449 B	12-06-2000
		JP 7501363 T	09-02-1995
		KR 261401 B	01-07-2000
		WO 9311290 A	10-06-1993
US 5802607 A	08-09-1998	NONE	
SU 1792517 A	30-01-1993	NONE	

EPO: OJ: 1982: 432

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82